

100 Clemson Research Blvd. Anderson, SC 29625 (864) 656-1094 Fax: (864) 656-1095 www.brickandtile.org



## Results of Tests on brick Conducted in accordance with C67/C67M - 21 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile

				12/10/2021				
Name:	The Belden Bric	Plant:		Canton				
	700 West Tuscarawas Street			•	led Date:	11/12/2021		
	Canton, OH 44702			Recei	ved Date:	11/12/2021		
Phone:	330-456-0031			Fired	Date:	11/12/2021		
Fax:	330-456-2694			Produ	Product Code:			
Report Number: 10484-25948			Lot Number:					
Description: Absorption	PLT 8 SHALE	NO ADDITIV	/E 75% FINE 2	E 25% COAF 3	RSE (THIN E	BRICK) 5	Average	Test Date
24 Hour Cold Water (%)		2.1	2.2	2.1	2.1	2.1	2.1	11/16/2021
5 Hour Boiling Water (%)		2.9	2.9	2.9	2.9	3.1	3.0	
Saturation Coefficient		0.70	0.78	0.73	0.71	0.67	0.72	
Efflorescence		11	12	13	14	15		Test Date
Efflorescence Detection		Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		12/9/2021

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 1088 - 20 Standard Specification for Thin Veneer Brick Units Made From Clay or Shale

Grade: Exterior, Interior

Michael Walker, Quality Manager

\*The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH The results shown above apply only to the samples tested, which are provided by the customer. This test report shall not be reproduced except in full, without written approval of the laboratory.