

TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org



Results of Tests on brick Conducted in accordance with C67/C67M - 23 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile

08/25/2023

Name:	The Belden Brick Company P. O. Box 430 Sugar creek, OH 44681	Plant:	Sugarcreek
Phone:	330-456-0031	Sampled Date:	8/8/2023
Fax:	330-456-2694	Received Date:	8/8/2023
Report Number:	11935-29718	Fired Date:	8/8/2023
		Product Code:	
		Lot Number:	

Description: **PLT 6 FIRECLAY & SHALE W/ADDITIVE (FACE)**

Absorption	1	2	3	4	5	Average	Test Date
24 Hour Cold Water (%)	4.7	4.7	5.2	5.0	5.1	4.9	8/10/2023
5 Hour Boiling Water (%)	6.4	6.3	6.8	6.5	6.5	6.5	
Saturation Coefficient	0.74	0.74	0.77	0.76	0.78	0.76	
Compressive Strength	1	2	3	4	5	Average	Test Date
psi	14,960	14,210	14,700	15,010	14,010	14,580	8/10/2023
IRA (Oven Dried Method)	6	7	8	9	10	Average	Test Date
g/min/30 in. ²	10.6	12.3	10.0	10.9	11.0	10.9	8/21/2023
Efflorescence	11	12	13	14	15	Test Date	
Efflorescence Detection	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		8/21/2023

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C216 - 22 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)
Grade: SW, MW

Katherine Hill
Katherine Hill, Quality Manager

**The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH
The results shown above apply only to the samples tested, which are provided by the customer.
This test report shall not be reproduced except in full, without written approval of the laboratory.*