

TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org



Results of Tests on brick Conducted in accordance with C67/C67M - 23a Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile

07/01/2024

Name:	The Belden Brick Company P. O. Box 430 Sugar creek, OH 44681	Plant:	Sugarcreek
Phone:	330-456-0031	Sampled Date:	6/5/2024
Fax:	330-456-2694	Received Date:	6/5/2024
Report Number:	12865-31927	Fired Date:	6/5/2024
		Product Code:	
		Lot Number:	

Description: **PLT 2, ALL SHALE W/ADDITIVE (PAVER, 2-3/4")**

Absorption	1	2	3	4	5	Average	Test Date
24 Hour Cold Water (%)	0.7	0.3	0.4	0.4	0.5	0.5	6/13/2024
5 Hour Boiling Water (%)	0.8	0.4	0.4	0.6	0.7	0.6	
Saturation Coefficient	0.81	0.75	0.79	0.75	0.77	0.77	

Compressive Strength	1	2	3	4	5	Average	Test Date
psi	27,010	27,650	27,620	27,050	27,490	27,360	6/14/2024

Efflorescence	11	12	13	14	15	Test Date
Efflorescence Detection	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	6/19/2024

Breaking Load	1	2	3	4	5	Average	Test Date
lb/in	827	2,366	2,333	2,712	2,432	2,134	6/19/2024

Abrasion Resistance	1	2	3	4	5	Average
	0.00	0.00	0.00	0.00	0.00	0.00

E303 Surface Friction	1	2	3	4	Average	Test Date
BPN	77	76	75	75	76	6/18/2024

Surface Temperature (F): 72
 Test Surface Location: BML
 Type of Slider: Rubber
 Condition of Slider: Good
 Test Surface Texture: Paver Extruded

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C216 - 23 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)
Grade: SW, MW

ASTM C902 - 22 Standard Specification for Pedestrian and Light Traffic Paving Brick
Class: SX, MX, NX
Type: I, II, III

ASTM C1272 - 22a Standard Specification for Heavy Vehicular Paving Brick
Type: F, R

Katherine Hill
Katherine Hill, Quality Manager

*The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH
 The results shown above apply only to the samples tested, which are provided by the customer.
 This test report shall not be reproduced except in full, without written approval of the laboratory.