

TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org

Results of Tests on brick Conducted in accordance with C67/C67M - 23a Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile

09/05/2024

Name:	The Belden Brick Company P. O. Box 430 Sugarcreek, OH 44681	Plant:	Sugarcreek
Phone:	330-456-0031	Sampled Date:	7/3/2024
Fax:	330-456-2694	Received Date:	7/3/2024
Report Number:	12943-32127	Fired Date:	7/3/2024

Description: **PLT 8, ALL FIRECLAY, NO ADDITIVE (PAVER, 2-1/4)**

Absorption	1	2	3	4	5	Average	Test Date
24 Hour Cold Water (%)	6.4	5.9	6.0	5.5	6.2	6.0	7/19/2024
5 Hour Boiling Water (%)	8.2	7.6	7.7	7.3	7.9	7.7	
Saturation Coefficient	0.78	0.78	0.77	0.76	0.79	0.77	
Compressive Strength	1	2	3	4	5	Average	Test Date
psi	16,240	16,700	15,900	15,530	16,010	16,080	7/16/2024
Efflorescence	11	12	13	14	15		Test Date
Efflorescence Detection	Not Effloresced		7/18/2024				
Breaking Load	1	2	3	4	5	Average	Test Date
lb/in	526	544	561	634	592	571	7/15/2024
Abrasion Resistance	1	2	3	4	5	Average	
	0.04	0.04	0.04	0.04	0.04	0.04	

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C902 - 22 Standard Specification for Pedestrian and Light Traffic Paving Brick
Class: SX, MX, NX
Type: I, II, III

ASTM C1272 - 22a Standard Specification for Heavy Vehicular Paving Brick
Type: R



Katherine Hill, Quality Manager

*The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH
The results shown above apply only to the samples tested, which are provided by the customer.
This test report shall not be reproduced except in full, without written approval of the laboratory.