





TEST REPORT

100 Clemson Research Blvd. Anderson, SC 29625 (864) 656-1094 Fax: (864) 656-1095 www.brickandtile.org

Results of Tests on brick Conducted in accordance with ASTM C 67-16 Standard Test Methods for Sampling and

05/16/2018									
Name:	The Belden Brick Company	Plant:	Sugarcreek	*Temperature: 60 - 90F					
Phone:	P. O. Box 430 Sugarcreek , OH 44681 330-456-0031 330-456-2694	Report Number:	8207-18727	*Humidity: 30% - 70%					
		Received Date:	05/02/2018						
		Sampled Date:	05/02/2018						
Fax:		Lot:							
		Product Code:							
Sample Description:	PLT 2, ALL SHALE NO ADDITIVE (PAVER, 2-1/4)								
				Test Date					

							Test Date
Absorption	1	2	3	4	5	Average	
24 Hour Submersion in Cold Water (%)	0.46	0.32	0.31	0.44	0.34	0.37	05/07/2018
5 Hour Submersion in Boiling Water (%)	0.61	0.45	0.44	0.57	0.40	0.49	
Saturation Coefficient (Ratio of 24H to 5H)	0.75	0.73	0.72	0.77	0.84	0.76	
Compressive Strength	1	2	3	4	5	Average	
psi	28,934	21,574	24,789	25,680	26,119	25,419	05/14/2018
MPa	199.5	148.7	170.9	177.1	180.1	175.3	
Breaking Load	6	7	8	9	10	Average	
(lb/in.)	1,777	1,708	1,529	1,640	1,686	1,668	05/07/2018
Efflorescence	11	12	13	14	15		
	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		05/15/2018
IRA (Oven Dried Method)	6	7	8	9	10	Average	
g/min/30 in. ²	2.1	1.9	2.2	2.0	2.3	2.1	05/07/2018
Abrasion Resistance	1	2	3	4	5	Average	
	0.00	0.00	0.00	0.00	0.00	0.00	05/07/2018

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 1272 - 17 Standard Specification for Heavy Vehicular Paving Brick

Type: R

ASTM C 902 - 15 Standard Specification for Pedestrian and Light Traffic Paving Brick

Class: SX, MX, NX, with absorption alternate in section 5.1.1.1

Type: I, II, III

1 A hay

Michael Walker, Quality Manager

*The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH The results shown above apply only to the samples tested, which are provided by the customer.

This test report shall not be reproduced except in full, without written approval of the laboratory.