



TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org

Results of Tests on brick Conducted in accordance with ASTM C 67-18 Standard Test Methods for Sampling and

Testing Brick and Structural Clay Tile

09/30/2020

Name:	The Belden Brick Company 700 West Tuscarawas Street Canton , OH 44702	Plant:	Canton	*Temperature: 60 - 90F
Phone:	330-456-0031	Report Number:	9739-23589	*Humidity: 30% - 70%
Fax:	330-456-2694	Received Date:	09/04/2020	
		Sampled Date:	09/04/2020	
		Lot:		
		Product Code:		

Sample Description: **PLT 6 FIRECLAY & SHALE, NO ADDITIVE (FACE)**

							Test Date	
Absorption		1	2	3	4	5	Average	
24 Hour Submersion in Cold Water (%)		4.19	4.34	4.38	4.34	4.42	4.33	
5 Hour Submersion in Boiling Water (%)		5.96	6.07	5.85	5.98	6.08	5.99	
Saturation Coefficient (Ratio of 24H to 5H)		0.70	0.71	0.75	0.72	0.73	0.72	
Compressive Strength		1	2	3	4	5	Average	
	<i>psi</i>	20,454	16,361	20,447	20,451	15,669	18,676	
	<i>MPa</i>	141.0	112.8	141.0	141.0	108.0	128.8	
Efflorescence		11	12	13	14	15		
		Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	09/18/2020	
IRA (Oven Dried Method)		6	7	8	9	10	Average	
	<i>g/min/30 in.²</i>	7.8	8.3	8.1	7.9	7.2	7.9	
Average % Void		20.7						09/17/2020

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 216 - 19 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)

Grade: SW, MW

Michael Walker, Quality Manager

**The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH*

The results shown above apply only to the samples tested, which are provided by the customer.

This test report shall not be reproduced except in full, without written approval of the laboratory.